

specific topic.

All use of STN is subject to the provisions of the STN Customer agreement. Please note that this agreement limits use to scientific research. Use for software development or design or implementation of commercial gateways or other similar uses is prohibited and may result in loss of user privileges and other penalties.

***** STN Columbus *****

FILE 'HOME' ENTERED AT 15:23:05 ON 01 AUG 2007

=> file caplus		
COST IN U.S. DOLLARS	SINCE FILE	TOTAL
	ENTRY	SESSION
FULL ESTIMATED COST	0.21	0.21

FILE 'CAPLUS' ENTERED AT 15:23:12 ON 01 AUG 2007

USE IS SUBJECT TO THE TERMS OF YOUR STN CUSTOMER AGREEMENT.

PLEASE SEE "HELP USAGETERMS" FOR DETAILS.

COPYRIGHT (C) 2007 AMERICAN CHEMICAL SOCIETY (ACS)

Copyright of the articles to which records in this database refer is held by the publishers listed in the PUBLISHER (PB) field (available for records published or updated in Chemical Abstracts after December 26, 1996), unless otherwise indicated in the original publications. The CA Lexicon is the copyrighted intellectual property of the American Chemical Society and is provided to assist you in searching databases on STN. Any dissemination, distribution, copying, or storing of this information, without the prior written consent of CAS, is strictly prohibited.

FILE COVERS 1907 - 1 Aug 2007 VOL 147 ISS 6

FILE LAST UPDATED: 31 Jul 2007 (20070731/ED)

Effective October 17, 2005, revised CAS Information Use Policies apply. They are available for your review at:

<http://www.cas.org/infopolicy.html>

*** YOU HAVE NEW MAIL ***

=> s jp 48038635/pn

L1 1 JP 48038635/PN
(JP48038635/PN)

=> d l1 ibib ab

L1 ANSWER 1 OF 1 CAPLUS COPYRIGHT 2007 ACS on STN

ACCESSION NUMBER: 1975:98831 CAPLUS Full-text

DOCUMENT NUMBER: 82:98831

TITLE: Polyester

INVENTOR(S): Chimura, Kazuchika; Ito, Kazuo; Takashima, Shunichi;

Shindo, Tamao; Kawashima, Masao

PATENT ASSIGNEE(S): Mitsubishi Rayon Co., Ltd.

SOURCE: Jpn. Tokkyo Koho, 4 pp.

CODEN: JAXXAD

DOCUMENT TYPE: Patent

LANGUAGE: Japanese

FAMILY ACC. NUM. COUNT: 2
PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
JP 48038635	B	19731119	JP 1969-59874	19690729 <--
BE 748781	A	19700916	BE 1970-748781	19700410
NL 7005224	A	19710202	NL 1970-5224	19700410

PRIORITY APPLN. INFO.:		
	JP 1969-59873	A 19690729
	JP 1969-59874	A 19690729

AB A catalyst mixture containing 0.005-0.2 weight % crystalline GeO₂ [1310-53-8] (particle diameter .apprx.100 μ) and Ca(OAc)₂ [62-54-4] or CaH₂ [7789-78-8] (0.4-1.5 Ca per Ge) as a solution in ethylene glycol (I), Sb [7440-36-0] (0.1-2.0 Sb per Ge; particle diameter <100 μ), and CaO, Zn(OAc)₂, or Mg(OAc)₂, and optionally containing triphenyl phosphate was useful for polycondensation of a composition containing dimethyl terephthalate (II) or mixts. of II and dimethyl isophthalate, and I to give polyesters with improved whiteness. Thus, a mixture containing II 200, I 150, Ca(OAc)₂ 0.1, and Sb 0.024 g was heated at 190-210° to cause ester-exchange reaction. After removal of MeOH formed the mixture was heated to 250° to remove excess I. A composition containing 0.04 g hexagonal GeO₂ and 0.04 g Ca(OAc)₂ in I was added and the mixture was heated 1 hr at 285° and 0.5 mm to give a white polymer [25038-59-9], intrinsic viscosity (1:1 PhOH-C₂H₂Cl₄ mixture, 25°) 0.782 and softening temperature 259°, compared to 0.674 and 252°, resp., for a polymer prepared from a similar composition in the absence of Sb, and 0.688 and 254°, resp., for a polymer prepared from a similar composition containing SbPh₃ instead of Sb; the amount of GeO₂ retained in the polymer was 87%, compared to 72% for similar polymerization without Sb.

=> logoff

ALL L# QUERIES AND ANSWER SETS ARE DELETED AT LOGOFF

LOGOFF? (Y)/N/HOLD:y

COST IN U.S. DOLLARS

SINCE FILE	TOTAL
ENTRY	SESSION
5.31	5.52

FULL ESTIMATED COST

DISCOUNT AMOUNTS (FOR QUALIFYING ACCOUNTS)

SINCE FILE	TOTAL
ENTRY	SESSION
-0.78	-0.78

CA SUBSCRIBER PRICE

STN INTERNATIONAL LOGOFF AT 15:23:58 ON 01 AUG 2007